



TEST REPORT

68, Gajaeul-ro, Seo-gu, Incheon, SEOUL 404-817 Rep. of KOREA

TEL 82-32-5709-700 FAX 82-32-575-5613

Report No : TAS-046365

Receipt Date : Sep.27.2013

Client : Oh Jangsoo

Test Completion Date : Oct.18.2013

LG HAUSYS Co., Ltd

150, Songjeong-dong, Hungduk-gu, Cheongju-city, Chungbuk, 361-721, Korea

Sample : Artificial Marble (SOLID)

TEST RESULTS

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) °C)	-	-	1.720	ASTM D792-08(Method A)
Rockwell Hardness(HRM)	-	-	88	ASTM D785-08(Procedure A)
Tensile Strength	MPa	-	42.4	ASTM D638-10(*)
Tensile Modulus of Elasticity	GPa	-	8.19	ASTM D638-10(*)
Flexural Strength	MPa	-	64.1	ASTM D790-10(**)
Flexural Modulus of Elasticity	GPa	-	10.0	ASTM D790-10(**)
Izod Impact Strength	J/m	-	16	ASTM D256-10(Method A)
Water Absorption(24 h Immersion)	%	-	0.02	ASTM D570-98(2010)e1
Appearance(Discoloration) After Heat Resistance((170±2) °C × 1 h)	-	-	No Defects	By The Client
Hot Water Resistance Test	-	-	No Defects	JIS K 6902 : 2007
Deflection Temperature Under Load(1.82 MPa)	°C	-	101	ASTM D648-07(Method B)
Thermal Expansion	1/°C	-	4.2×10□□	JIS K 6911 : 1995
Pencil Hardness(Mitsu bishi pencil)	-	-	6H	KS M ISO 15184 : 2002

* Specimen: Type I, Speed of Testing: 5 mm/min(Modulus: 1 mm/min)

** Speed of Testing: 5.5 mm/min, Support Span: 200 mm

USAGE : QUALITY CONTROL

- Next Page -

Cho Hyeong-gil

Prepared by Cho Hyeong-gil
Tel: +82-32-570-9737
E-mail: gil@ktr.or.kr

Chung Eungsoo

Reviewed by Chung Eungsoo
Technical Manager
E-mail: chali@ktr.or.kr

Oct.18.2013

Korea Testing & Research Institute

President





TEST REPORT

68, Gajaeul-ro, Seo-gu, Incheon, SEOUL 404-817 Rep. of KOREA

TEL 82-32-5709-700 FAX 82-32-575-5613

Report No : TAS-046365

Receipt Date : Sep.27.2013

Client : Oh Jangsoo

Test Completion Date : Oct.18.2013

LG HAUSYS Co., Ltd

150, Songjeong-dong, Hungduk-gu, Cheongju-city, Chungbuk, 361-721, Korea

Sample : Artificial Marble (SOLID)

TEST RESULTS

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- NOTE :
1. The test results on this test report are only limited to the samples and sample names provided by the customer and KTR do not guarantee the quality of all products of the customer.
 2. This test report shall not be used for public relation, advertisement, lawsuit and any other purposes outside the scope of its defined usage.
 3. This test report includes the test result performed in accordance with the test method which is presented by client.

Cho Hyeong-gil

Prepared by Cho Hyeong-gil
Tel: +82-32-570-9737
E-mail: gil@ktr.or.kr

Chung Eungsoo

Reviewed by Chung Eungsoo
Technical Manager
E-mail: chali@ktr.or.kr

Oct.18.2013

Korea Testing & Research Institute

President

Choi Hyeong-gil

2 of Total 2 Page(s)

전자문서본(Electronic)

